


Test Report



No:260013653

Verification Website: www.gttctech.com

Verification Code: JADJ-5645-14

Scan to download



Issue Date:2026-03-25

Applicant: LLC UMINEX

Address: 212021, Republic of Belarus, Mogilev, Altayskaya str., 4B

Information confirmed by applicant:

Non-woven material (UMINEX ADL-TECH)

Quantity: 0.83kg

Basis of judgement:

Date Received/Date Test Started: 2026-03-16

Conclusion:

pH value

Width

Mass per unit area

Breaking strength

Elongation at break

Note: "M"-Meet the standard's requirement "F"-Fail to meet the standard's requirement
"---"-No comment

Remark:

All the tested items are tested under the standard condition (except for indication).

Copies of the report are valid only re-stamped.

The experiment was carried out at No.1, Zhujiang Road, Panyu District, Guangzhou, Guangdong, P.R.China.

Approved By:

Hongmin Lai

HongMin Lai Engineer



Test Report

No:260013653



Headquarters: No.1, Zhujiang Road, Panyu District, Guangzhou, Guangdong, P.R.China.

Tel: +86-20- 61994598/61994599

Huadu Laboratory: No.1, Hebin West Road, Qiling, Huadu District, Guangzhou, Guangdong, P.R.China.

Tel: +86-20- 37721161/66348638

Test Report

No:260013653

pH value(ISO 3071:2020, 0.1mol/L KCl extracting solution)
6.7

Width(m)

(ISO 22198:2006)

Full width

Average 0.09

Minimum 0.09

Mass per unit area(g/m²)

(ISO 9073-1:2023)

43.6

Breaking strength(N)

(ISO 9073-3:2023, The distance between the clamps: 50mm)

MD 45

CD 52

Elongation at break(%)

(ISO 9073-3:2023, The distance between the clamps: 50mm)

MD 45

CD 70

—End of Report—

Page 3 of 5



Note

1. The report is invalid without authorized stamp.
2. Copies of this report are invalid without authorized stamp.
3. Any dispute should be raised within 15 days after receiving the report.
4. The result is only valid for the tested sample.
5. The results of unapproved items are for reference only.
6. This report is invalid if altered.
7. Our company does not accept any responsibility for the authenticity of the information supplied by customers (including sample information).
8. The report shall not be duplicated separately or partly, without prior written permission approved by GTTC, except duplicated in full version.